

# Primary lithium batteries

## G 22/6

3.0 V Primary lithium-sulfur dioxide (Li-SO<sub>2</sub>)

High drain capability

DD-size spiral cell



### Benefits

- High and stable discharge voltage
- Very high pulse capability
- Performance not affected by cell orientation
- Long storage possible before use
- Ability to withstand extreme temperature

### Key features

- Low self-discharge rate  
*(less than 3% after 1 year of storage at +20°C)*
- Hermetic glass-to-metal sealing
- Built-in safety vent  
*(at the negative end of the cell)*
- Meets shock, vibration and other environmental requirements of military specifications
- Made in UK

### Main applications

- Radiocommunications and other military applications
- Professional electronics

### Cell size reference

DD

### Electrical characteristics

*(typical values relative to cells stored for one year or less at +30°C max.)*

Nominal capacity 16.5 Ah  
*(at 0.5 A +20°C 2.0 V cut off. The capacity restored by the cell varies according to current drain, temperature and cut off)*

Open circuit voltage (at +20°C) 3.0 V

Nominal voltage (at 1.0 A +20°C) 2.8 V

Maximum recommended continuous current (to avoid overheating) 3 A

Pulse capability : Typically up to 10 A.  
*(The voltage readings may vary according to the pulse characteristics, the temperature and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult Saft)*

Storage *(recommended possible without leakage)* +30°C (+86°F) max  
+85°C (+185°F) max

Operating temperature range -60°C/+70°C  
*(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)*  
(-76°F/+158°F)

### Physical characteristics

Diameter (max) 33.3 mm (1.31 in)

Height (max) 120.6 mm (4.75 in)


Typical weight 175 g (6.18 oz)

Li metal content 5.3 g

Standard cell comes with protruding positive end-cap.  
Finish with tabs available on request.



# G 22/6



Overall dimensions in mm

## Handling precautions


- Cell is pressurised.
- Do not puncture, open or mutilate.
- Do not obstruct the safety vent mechanism.
- Do not short circuit or charge.
- Do not expose to fire or temperatures above +70°C (+158°F).

## Saft Specialty Battery Group


12, rue Sadi Carnot  
93170 Bagnolet - France  
Tel +33 (0)1 49 93 19 18  
Fax +33 (0)1 49 93 19 69

River Drive, South Shields  
Tyne and Wear, NE33 2TR - UK  
Tel +44 (0)191 456 14 51  
Fax +44 (0)191 456 63 83


[www.saftbatteries.com](http://www.saftbatteries.com)



Voltage at mid-discharge versus Current and Temperature (2.0 V cut-off)



Typical discharge profiles at +20°C



Capacity versus Current and Temperature (continuous discharges 2.0 V cut-off)

Doc. N° 31061-2-1005

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft.

For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2.

Published by the Communications Department.

Photo credit: Saft.

Société anonyme au capital de 31 944 000€

RCS Bobigny B 383 703 873

Produced by Arthur Associates.



**SAFT**